

DATA SHEET / SPECIFICATION VS60 70

Description:

A Viscoelastic, temperature sensitive foam for use in mattress applications. Complies with the requirements of Schedule 1, Part 1, The Furniture and Furnishings (Fire) (Safety) Amended Regulations 1989.

VS60 70		
Property	Test Procedure	VS60 70
Density Range	BS EN ISO 845:1995	57-61 kg/m ³
Hardness (40%) Strength	BS EN ISO 2439	60-90N
Nominal Tensile Strength	BS EN ISO 1798	90 kPa min.
Nominal Elongation at Break	BS EN ISO 1798	120%
Resilience	BS EN ISO 9307:2007	25% max
Recovery rate		5-20 secs.
Compression set		15% max

Standard colour is white.

The Vita Group reserves the right to update product data information without prior notice.

Issued 03/2021.