

Wira House, West Park Ring Road,

Leeds, LS16 6QL, UK. Telephone: +44 (0)113 259 1999

Email: <a href="mailto:info@bttg.co.uk">info@bttg.co.uk</a>
Website: <a href="mailto:www.bttg.co.uk">www.bttg.co.uk</a>

Date: 12 April 2018

Our Ref: 54837-5 Your Ref: 0001012437

Page: 1 of 3

Client: Vita Cellular Foams (UK) Limited

Oldham Road Middleton Manchester M24 2DB

Job Title: Ignitability Test For Foam

Client's Order No: 0001012437

Date of Receipt: 28 March 2018 Date of Test Start: 12 April 2018

Description of Sample(s): One sample identified as follows was received for testing:

CM14.0 Ref. 120118

Work Requested: We were asked to make the following test:

Schedule 1 Part 1 of the Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No. 1324 (as amended by SI 1989 No. 2358, SI 1993 No. 207 & SI 2010 No. 2205),

Ignitability test for foam.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0)113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 12 April 2018

Our Ref: 54837-5 Your Ref: 0001012437

Page: 2 of 3

### Vita Cellular Foams (UK) Limited

Sample was identified as follows:

CM14.0 Ref. 120118

Schedule 1 Part 1 of the Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No. 1324 (as amended by SI 1989 No. 2358, SI 1993 No. 207 & SI 2010 No. 2205), Ignitability test for foam.

### Conditioning

All materials used were conditioned in the environments specified in Clause 5 of BS 5852: 1990 Methods of test for the ignitability of upholstered composites for seating by flaming sources.

#### **Testing**

The material was tested according to BS 5852: Part 2: 1982. Methods of test for the ignitability of upholstered composites for seating by flaming sources against Ignition Source 5 under a cover fabric corresponding to the standard FR polyester woven fabric specified in the above regulations.

It should be noted that the results of BS 5852: Part 2: 1982 relate only to the ignitability of the combination of materials under test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

The results for all tests are given in the table(s) on the following page(s).

Uncertainty of measurement has not been taken into account when presenting the test result. The overall uncertainty budget for BS 5852: Part 2: 1982 is as follows:

Measurements:  $\pm 2 \text{ mm}$ Timings:  $\pm 2 \text{ seconds}$ Weight:  $\pm 1 \text{ g}$ 

(

Reported by:.

Countersigned By:..
P Doherty

J Coleman \

Fire Technician Operational Head

Enquiries concerning this report should be addressed to Customer Services.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0)113 259 1999

Email: <a href="mailto:info@bttg.co.uk">info@bttg.co.uk</a>
Website: <a href="mailto:www.bttg.co.uk">www.bttg.co.uk</a>

Date: 12 April 2018

Our Ref: 54837-5 Your Ref: 0001012437

Page: 3 of 3

## Vita Cellular Foams (UK) Limited

# **RESULTS**

Sample Ref: CM14.0 Ref. 120118

Specimen No.	1	2
Initial mass of assembly (g)	10414	10316
Final mass of assembly (g)	10390	10294
Mass loss (g)	24	22

Criteria: mass loss is less than 60 g.

# Conclusion

The foam meets the requirements of Schedule 1 Part 1 of the Furniture and Furnishings (Fire) (Safety) Regulations 1988 (as amended) S.I. No. 1324.

