

Wira House, West Park Ring Road,

Leeds, LS16 6QL, UK. Telephone: +44 (0)113 259 1999

> Email: info@bttg.co.uk Website: www.bttg.co.uk

Date: 06 January 2020

 Our Ref:
 23/57137-1

 Your Ref:
 0001014159

Page: 1 of 3

Client: Vita Cellular Foams (UK) Limited

Oldham Road Middleton Manchester M24 2DB

Job Title: Ignitability Test For Foam

Client's Order No: 0001014159

Date of Receipt: 13 December 2019
Date of Test Start: 02 January 2020

Description of Sample(s): One sample of foam identified as follows was received for testing:

Recon 6.0CM ref 091219

Work Requested: We were asked to make the following test:

Schedule 1 Part 1 of the Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No. 1324 (as amended by SI 1989 No. 2358, SI 1993 No. 207 & SI 2010 No. 2205),

Ignitability test for foam.





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk Website: www.bttg.co.uk

Date: 06 January 2020

Our Ref: 23/57137-1 Your Ref: 0001014159

Page: 2 of 3

Vita Cellular Foams (UK) Limited

Sample was identified as follows:

Recon 6.0CM ref 091219

Schedule 1 Part 1 of the Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No. 1324 (as amended by SI 1989 No. 2358, SI 1993 No. 207 & SI 2010 No. 2205), Ignitability test for foam.

Conditioning

All materials used were conditioned in the environments specified in Clause 5 of BS 5852: 1990 Methods of test for the ignitability of upholstered composites for seating by flaming sources.

Testing

The material was tested according to BS 5852: Part 2: 1982. Methods of test for the ignitability of upholstered composites for seating by flaming sources against Ignition Source 5 under a cover fabric corresponding to the standard FR polyester woven fabric specified in the above regulations.

It should be noted that the results of BS 5852: Part 2: 1982 relate only to the ignitability of the combination of materials under test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

The results for all tests are given in the table(s) on the following page(s).

Uncertainty of measurement has not been taken into account when presenting the test result. The overall uncertainty budget for BS 5852: Part 2: 1982 is as follows:

Countersigned By:.....

Measurements: ± 2 mm
Timings: ± 2 seconds

Weight: ± 1 g

Reported by:

B Bland P Doherty
Laboratory Technician Manager

Enquiries concerning this report should be addressed to Customer Services





Wira House, West Park Ring Road,

Leeds, LS16 6QL, UK. Telephone: +44 (0)113 259 1999

> Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 06 January 2020

Our Ref: 23/57137-1 Your Ref: 0001014159

Page: 3 of 3

Vita Cellular Foams (UK) Limited

RESULTS

Sample Ref: Recon 6.0CM ref 091219

Specimen No.	1	2
Initial mass of assembly (g)	6837	6885
Final mass of assembly (g)	6812	6859
Mass loss (g)	25	26

Criteria: mass loss is less than 60g.

Note: This report relates only to the samples submitted and as described in the report.

Conclusion

The foam meets the requirements of Schedule 1 Part 1 of the Furniture and Furnishings (Fire) (Safety) Regulations 1988 (as amended) S.I. No. 1324.

