

DATA SHEET / SPECIFICATION

FV50 55

Description:

TCPP free combustion modified viscoelastic polyether polyurethane foam which is suitable for mattress applications. Complies with the requirements of Schedule 1 Part 1 of The Furniture and Furnishing (Fire) (Safety) Amended Regulations 1989. FRee offers reduced odour and scorch free whilst maintaining comfort and durability.

FV50 55		
Property	Test Procedure	FV50 55
Density Range	BS EN ISO 845:1995	48-52 kg/m ³
Hardness (40%) Strength	BS EN ISO 2439	40-70N
Nominal Tensile Strength	BS EN ISO 1798	Min 50kPa
Nominal Elongation at Break	BS EN ISO 1798	Min 90%
Nominal Resilience		Max 16%
Nominal Recovery Rate		3-30 seconds

Standard colour is cream.

The Vita Group reserves the right to update product data information without prior notice.

Issued 05/2020.