



DATA SHEET / SPECIFICATION

VS60 70

Description:

A viscoelastic foam for use in mattress and medical seating applications. Complies with the requirements of Schedule 1, Part 1, The Furniture and Furnishing (Fire) Safety) Amended Regulations 1989.

VS60 70		
Property	Test Procedure	VS60 70
Density Range	BS EN ISO 845:1995	57-61 kg/m ³
Hardness (40%) Strength	BS EN ISO 2439	60-90N
Recovery Rate		5-20 seconds
Compression Set	BS EN ISO 1856	15% max

Standard colour is white.

The Vita Group reserves the right to update product data information without prior notice.

Issued 05/2020.