



# Confidential Report

**Our Ref: 23/62118C/05/24**





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 07 June 2024

Our Ref: 23/62118C/05/24  
Your Ref: 1017868

Page: 1 of 3

**Client:** Vita Cellular Foams (UK) Limited

Oldham Road  
Middleton  
Manchester  
M24 2DB

**Job Title:** Fire Test on One Foam Sample

**Clients Order Ref:** 1017868

**Date of Receipt:** 31 May 2024

**Date Test Started:** 06 June 2024

**Description of Sample:** One sample of foam, which was referenced by the client as;  
Novus 12CM

**Work Requested:** We were asked to make the following fire test:

Schedule 1 Part 1 of the Furniture and Furnishings (Fire) (Safety) Regulations 1988,  
Ignitability test for foam.

- \* subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited

Note: This report relates only to the items tested.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2024 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 07 June 2024

Our Ref: 23/62118C/05/24  
Your Ref: 1017868

Page: 2 of 3

Client: Vita Cellular Foams (UK) Limited

## Schedule 1 Part 1 of the Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No. 1324 (as amended by SI 1989 No. 2358, SI 1993 No. 207 & SI 2010 No. 2205), Ignitability test for foam.

### Conditioning

All materials used were conditioned in the environments specified in Clause 5 of BS 5852: 1990 Methods of test for the ignitability of upholstered composites for seating by flaming sources.

### Testing

The material was tested according to BS 5852: Part 2: 1982. Methods of test for the ignitability of upholstered composites for seating by flaming sources against Ignition Source 5 under a cover fabric corresponding to the standard FR polyester woven fabric specified in the above regulations.

It should be noted that the results of BS 5852: Part 2: 1982 relate only to the ignitability of the combination of materials under test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

### Results

Specimen No.	1	2
Initial mass of assembly (g)	10300	10298
Final Mass of assembly (g)	10279	10275
Mass loss (g)	21	23
Flaming Duration (mins/secs)	3.11	3.58
Smouldering Duration (mins/secs)	5.47	5.54

Criteria: mass loss is less than 60g.  
flaming duration is less than 10 mins  
smouldering duration is less than 60 mins





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [onestopshop@bttg.co.uk](mailto:onestopshop@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 07 June 2024

Our Ref: 23/62118C/05/24  
Your Ref: 1017868

Page: 3 of 3

**Client:** Vita Cellular Foams (UK) Limited

## Conclusion

The foam meets the requirements of Schedule 1 Part 1 of the Furniture and Furnishings (Fire) (Safety) Regulations 1988 (as amended) S.I. No. 1324.


Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

## Uncertainty Budget

Timings:  $\pm 2$  seconds.  
Weights:  $\pm 2g$ .

Reported by:  R Walls, Laboratory Technician

Countersigned by:  B Bland, Technical Customer Service Officer

Enquiries concerning this report should be addressed to Customer Services.

